

## SB-200 HIGH TEMP RED RTV SILICONE SEALANT

**DESCRIPTION:** Premium, high temperature, one component RTV acetoxy cure silicone sealant and adhesive. When fully cured, this unique VOC compliant formula offers tenacious adhesion to form waterproof and airtight bonds to materials in high temperature scenarios. This product is specifically formulated to offer all weather performance to meet today's Green Building Standards.

**SUBSTRATES:**

- Metal
- Steel
- Tile
- Ceramic
- Glass
- Aluminum
- Painted Surfaces
- Marble
- & More

**LIMITATIONS:** Not intended for continuous under-water use. Not recommended for structural glazing.

**APPLICATION:** Interface and surfaces must be clean, dry, and free of dust, dirt, oil and water-proofing and release agents. Cut cartridge nozzle at slant and puncture inner seal. Apply bead size as desired. Apply uniform bead with steady pressure. Tool within ten minutes of application. Sealant starts to skin over in ten minutes and dries to the touch in an hour.

**CLEANING:** While uncured, remove excess material from tools with Xylene. After curing, rubber can be cut away. For cleaning pump tools while wet, use 1-1-1 chlorinated solvent. See cautions on cleaner labels.

**FEATURES & BENEFITS:**

- High Temp Performance
- Excellent Weatherability
- UV Stable
- Non-Yellowing
- VOC Compliant
- Non-Flammable
- Waterproof
- Excellent Adhesion
- Non-Shrinking

**APPLICATIONS:**

- Sealing & Glazing
- HVAC/R
- Plumbing
- Roofing
- Kitchen & Bath
- Furnace & Fireplace
- Flues & Venting
- Transportation Seals
- Appliance Trim
- Above Grade

**SHELF LIFE:** 24 months.

**STORAGE:** Unopened containers should be kept in dry areas between 40°F and 90°F. Rotate stock.

**CAUTION:** For industrial use only. Skin and eye irritant. Harmful if swallowed. Avoid contact with or breathing in of vapor, and use adequate ventilation. Material on skin should be wiped and washed off with soap and water. For eyes, flush with water and seek medical attention. SEE SAFETY DATA SHEET.

**PACKAGING:** 10.3 fl. oz. cartridge, 5 gallon pail.

**COLOR:** Red

**SPECIFICATIONS:**

VOC	30 g/l	
Temperature Range	-62° to 500°F	
Intermittent Temperature Range	650°F	
Skin Over Time (min)	10*	MNA Method
Tack Over Time (min)	17*	ASTM C-679
Cure Rate	1/8" per 24hrs*	MNA Method
Tensile Strength (psi)	310	ASTM D-412
Elongation %	500	ASTM D-412
Durometer Shore A	26	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	

\*All values are typical at 77°F, 50% R.H. unless otherwise noted.  
 MEETS SPECIFICATIONS: ASTM C920 Type S, NS, Class 25; TT-S-00230C (COM-NBS), TT-S-01543A (COMNBS), MIL-A-46106A, FDA CFR 177.2600, USDA Approved, NSF 51, UL Recognized Component.

Revised: 5/1/23