SUREBOND TECHNICAL DATA SHEET SB-188

SB-188 HIGH TEMPERATURE SILICONE SEALANT

FEATURES:

• Flexible

• Fast cure

extreme temperatures

Can withstand

• High-strength

• Non-flammable

Highly functional

DESCRIPTION: Non-flammable, fast-curing, high solids sealant. Insulates electrically and thermally. Weather-proof. USDA approved.

USES:

Industries

- Automotive
- Marine
- HVAC
- Construction
- Plumbing
- Architectural
- Electrical

- **Substrates**
- Metal
- Plastics
- Fiberglass
- Glass
- Wood
- Painted surfaces
- Rubbers

APPLICATION: Interface and surfaces must be clean, dry and free of dust, dirt, oil and water-proofing and release agents. Cut cartridge nozzle at slant and puncture inner seal. Apply bead size as desired. Apply uniform bead with steady pressure. Tool within five minutes of application. Sealant starts to skin over in five minutes and dries to the touch in an hour.

CLEANING: While uncured, remove excess material from tools with Xylene. After curing rubber can be cut away. For cleaning pump tools while wet, use 1-1-1 chlorinated solvent. See cautions on cleaner labels.

SPECIFICATIONS:

VOC Cure Time Tack-free Time Tensile Strength Elongation Staining Hardness, Shore A **Dielectric Strength Functional Range Application Range**

30 g/l 24 Hours 10-20 Minutes 325 PSI 550% fully cured None 25-28 550 volts at/mil at 77° F -75° F to +500° F -20° F to +122° F

BENEFITS:

- Durable bond to material
- Allows for movement of dissimilar materials within functional temperature range.
- Excellent for high temperature uses
- Easy application
- Easy to match substrate
- Effective from -75° F to +500° F

SHELF LIFE: 12 months.

STORAGE: Unopened containers should be stored in a cool, drv area.

CAUTION: For industrial use only. Skin and eye irritant. Harmful if swallowed. Avoid contact with or breathing in of vapor and use adequate ventilation. Material on skin should be wiped and washed off with soap and water. For eyes, flush with water and seek medical attention.

SEE MATERIAL SAFETY DATA SHEET. **PACKAGING:** 10.3 oz. tube **COLORS:** Clear, Black

> 2.97% by weight 1/8" bead ASTM-C679 Test Method ASTM-D412 Test Method ASTM-D412 Test Method TT-S-00230C Test Method TT-S-00230C Test Method

All values are typical at 75° F, 50% R.H. unless otherwise noted. Federal Specifications TT-S-00230C used when applicable.

